

Pink® Batts: Wall

Thermal insulation for residential wall applications

Description

Pink® Batts are made from flexible and resilient glasswool for thermal and acoustic insulation of residential walls. Pink® Batts are available in various sizes and densities to fit standard timber and steel stud spacings.

Application

Pink® Batts are the trusted choice when it comes to constructing new homes or retrofitting existing buildings for increased thermal efficiency. The Pink® Batts insulation range is available in various thermal R-values and dimensions ensuring there is an effective and efficient product solution for every application.

Pink® Batts, renowned for their firmness, are low itch, easy to cut and friction fit standard wall studs to make homes feel cooler in summer, warmer in winter and provide energy savings all year round.

Features and benefits

Firm to fit	→	Friction fit to stay in place without slumping, for continual thermal performance.
Recover to their natural thickness quickly	→	You can be assured the batts will meet their required thermal performance.
Australian made using up to 80% recycled content	→	Made for Australian conditions.

Physical characteristics

	Material R-value m ² K/W	Nominal thickness mm	Width mm	Length mm	Batts per pack	m ² per pack	Coverage per pack m ²	Packs per Bale	Product code
Wall	R1.5	70	430	1160	24	12.0	13.6	6	900166
			580	1160	24	16.1	18.2	6	900167
	R2.0	90	430	1160	24	12.0	13.6	5	901217
			580	1160	24	16.1	18.2	5	901218
	R2.2	90	430	1160	16	8.0	9.0	6	901220
			580	1160	16	10.8	12.2	6	901221
	R2.0 HD	70	430	1160	12	6.0	6.8	6	900210
			580	1160	12	8.1	9.1	6	900211
			600	1200	12	8.6	8.6	6	900213
	R2.5 HD	90	430	1160	12	6.0	6.8	5	900253
			580	1160	12	8.1	9.1	5	900256
			600	1200	12	8.6	8.6	6	900214
R3.6 HD	130	600	1200	6	4.3	4.9	5	900216	

Physical properties

Property	Test method/standard	Result	Unit
Maximum service temperature	ASTM C411/C447	350	°C
Thermal resistance	AS/NZS 4859.1	Complies	m ² K/W
Moisture absorption	When exposed to environmental conditions of 50°C and 95% relative humidity for four days	< 0.2%	% by volume
pH	ASTM C871	9 (does not contribute to the corrosion of steel structures)	-

Fire hazard properties

Property	Test method/standard	Result
Combustibility	AS1530.1	Non-combustible
Early Fire Hazard Indices	AS/NZS 1530.3	
Ignitability Index		
Spread of Flame Index		
Heat Evolved Index		
Smoke Developed Index		
BAL Compliance	AS3959	Low-FZ

Acoustic performance

Sound absorption

Pink® Batts tested achieve the following sound absorption coefficients when tested in accordance with AS ISO 354-2006.

Property	Thickness mm	Sound absorption coefficients at frequencies (Hz) of:						NRC	α _w
		125	250	500	1000	2000	4000		
Pink® Batts R2.0	90	0.40	0.79	1.03	0.97	0.94	0.92	0.95	1.0

Flow resistivity

Pink® Batts tested achieve the following flow resistivities when tested in accordance with ASTM C522-03.

Property	Test method/standard	Test results				Unit	
		Thickness mm	R-Value	70	90		
Airflow resistance of acoustic materials	ASTM C522-03	70	1.5	4730	11750	7930	RAYLS/m

Health and safety

Fletcher Insulation glasswool products are manufactured from FBS-1 Glasswool Bio-Soluble Insulation®. FBS-1 Glasswool Bio-Soluble Insulation® is safe to use and is classified as non-hazardous according to the criteria of Safe Work Australia. Fletcher Insulation glasswool insulation can be used with confidence in any residential, commercial or industrial application.

Environmental properties

Fletcher Insulation avoids the use of Ozone Depleting Potential (ODP) substances in the manufacture or composition of its FBS-1 Glasswool Bio-Soluble Insulation®.

The use of these Fletcher Insulation products guarantees the use of Zero ODP insulation while also ensuring that no harmful levels of Volatile Organic Compounds (VOCs) are released. This allows the incorporation of environmentally preferable insulation whilst also maintaining indoor air quality.

Technical specification

When specifying, state the following:

The insulation material shall be Fletcher Insulation Pink® Batts Wall R _____ m²K/W (Material R-value)
_____ (thickness) x _____ (width) x _____ (length) mm.

© Fletcher Insulation Pty Limited 2019. Fletcher Insulation reserves the right to change product specifications without prior notification. Information in this publication and otherwise supplied to users as to the subject product is based on our general experience and is given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or is to be implied with respect to either such information or the product itself, in particular the suitability of the product for any particular purpose. The purchaser should independently determine the suitability of the product for the intended application. The colour PINK, Pink® and Pink® Batts are registered trademarks of Owens Corning used under licence by Fletcher Insulation. FBS-1 Glasswool Bio-Soluble Insulation® is a registered trademark of ICANZ. Unless otherwise stated all ™ and ® are trademarks and registered trademarks of Fletcher Insulation Pty Limited ABN 72 001 175 355.